



# Chiragum Trasparente

## Non-walkable elastomeric one-component membrane

Transparent waterproofing liquid membrane, composed by a resin mix and proper additives in order to give the product excellent waterproofing features and high elasticity.

### *Use*

Engineered to avoid water infiltrations and protect surfaces, leaving the support visible or pre-existent flooring.

Applicable on rooftops, terraces and balconies.

### *Application Cycle*

#### **Support preparation**

Substrate must be perfectly dry and cured. Surfaces must be perfectly clean, dry, free from dust and incoherent parts; the support must be structurally stable, free from efflorescences and rising damp. Remove any failing, detaching part. In the presence of oily substances, remove them meticulously. In the presence of microflora is necessary to remove it by mechanical action. It is recommended to brush vigorously and dust out the support in order to obtain a good adhesion.

#### **Application**

The product is ready to use, apply with brush or roller waiting 8 hours between coatings. It is recommended to apply on days free from rain for at least 48 hours.

### *Recommendations*

Make sure the supports are perfectly dry and clean. Wait the first coating to be perfectly dry before proceeding to next coatings. Do not apply in risk of rain for at least 48 hours. In case of very hot days, a natural slight stickiness of the coating may occur. Do not apply below 10°C or above 35°C. It is recommended to protect the coatings until completely dry.

### *Technical data*

---

**Application:** brush - roller

---

**CHIRAEMA**

Contrada S. Maria Paradiso - 91026 Mazara del Vallo (TP)  
Tel: (+39) 0923 947363 - Fax: (+39) 0923 948548

**Packaging:** 11 - 14 - 113

---

**Colour:** trasparente

---

**Consistency:** thixotropic paste

---

**Yield:** approx. 2 sqm/l per 2 coats

---

**Dilution:** ready to use

---

**Application temperature:** from +10°C to +35°C

---

**Abrasion resistance:** dried 18-24 hr - hardened 2 days (T=25°C e U.R.:65%)

---

**Density:** 1.1 ±0.1 kg/dm<sup>3</sup>

---

**Resistance:** excellent to water, atmospheric agents and temperature changes

---

**Waiting time before further layers:** after 24 hr

---

**Tools cleaning:** water soon after use

---

**VOC:** < 140 g/l (2010) - Cat. i: Cat. i: One-pack performance coatings - water-base (Dir. 2004/42/CE)

---

**Pallet:** 33 drum of L 13

---

Data contained in technical data sheets refer to laboratory tests. Indications and methods may be subject to change over time, depending on any technological and productive improvements. Products application takes place out of our control, as we cannot directly intervene on the conditions of the construction sites and on the execution of the works. All indications are general and do not bind our company in any way and therefore the responsibility falls exclusively on customer. We recommend a preventive test of the product in order to verify the suitability in relation to its particular use. Technical service is available to provide additional information.