



Decorsan

Sanitizing water paint

Acrylic water paint for indoor usage, washable, high mold killing features, easy to brush and satin look.

Use

Used to prevent mold formation in subjected domestic and industrial environments.

Applicable on any type of indoor support, properly prepared:

- Smoothing products
- Consistent paints and coatings
- Fine plasters
- Gypsum surfaces and plasterboards

Application Cycle

Support preparation

On new mural surfaces: Make sure the support is perfectly dry and cured. Remove the dust from surfaces, apply a coat of fixative product (Isoplast Acrilico) and let dry.

On pre-treated mural surfaces: Carefully remove any peeling paint, traces of oil and grease. Level any irregularity from the support and treat holes and cracks with Monostucco. Sand the fillings and recovers, dust out, apply a coat of fixative product (Isoplast Acrilico) and let dry (about 6-12 hours, depending on weather conditions).

On surface with presence of molds: Treat with PRO 01 detergent and let dry. After 4-5 hours proceed with the application of one coat of specific insulating fixative PRO 02 and let dry (about 6 hours, depending on weather conditions).

Application

Apply, properly diluted, with a roller, brush or spray waiting at least 4-5 hours between coats.

Recommendations

Even if top notch substances are used, it is not possible to assure a total, definitive action against all micro-organisms in nature and environmental conditions. Do not add apply on wet or non cured supports. Do not apply below 5°C or above 35°C. Use clean water for dilution. It is recommended to protect from dust until complete desiccation. Maximum washability is achieved after 15 days from application.

CHIRAEMA

Contrada S. Maria Paradiso - 91026 Mazara del Vallo (TP)
Tel: (+39) 0923 947363 - Fax: (+39) 0923 948548

Technical data

Application: airless - brush - roller

Packaging: l 2.5 - l 4 - l 14

Colour: white - tinted by means of the Tintometric System Color Meter Pro

Gloss: satin

Dilution by volume: with water: 1st coat approx. 30-40% - 2nd coat approx. 20-30%

Application temperature: from +5°C to +35°C

Coverage: excellent

Recoat time: after 4-5 hr

Drying: dried 4-5 hr - hardened 8-12 hr

Washability: after 15 days

Density: 1.65 ±0.05 kg/l EN ISO 2811-1

Theoretical Yield: approx. 10-12 sqm/l for coat

Tools cleaning: water soon after use

VOC: < 30 g/l (2010) - Cat. a: matt coatings for interior walls and ceilings - water-base (Dir. 2004/42/CE)

Pallet: 33 drums of L 14

Data contained in technical data sheets refer to laboratory tests. Indications and methods may be subject to change over time, depending on any technological and productive improvements. Products application takes place out of our control, as we cannot directly intervene on the conditions of the construction sites and on the execution of the works. All indications are general and do not bind our company in any way and therefore the responsibility falls exclusively on customer. We recommend a preventive test of the product in order to verify the suitability in relation to its particular use. Technical service is available to provide additional information.